

BOUNCE

SCHEMA TECNICA (secondo norma UNI EN ISO 14465)

Articole:	VGT 2843 TF COTONE ACCOPPIATO	
Composition:	63%PL 31% CO 6%EA	
weight g/m lin.:	1000 gr/mtl	
widht cm:	140	
- abrasion resistance - Martindale UNI EN ISO 12947-2 + EN 14465, appendice A	color degradation after 3000 giri: 4/5 color degradation after 6000 giri: 4/5 END POINT (rubs): >25.000	
Pilling resistance by the modified martindale method UNI EN ISO 12945-2	degradation average photographic scale 1/5 : 3/4 At 2000 giri: 3	
colour fastness to light UNI EN ISO 105-B02	Blue scale 1/8 result: 4/5	
colour fastness to rubbing UNI EN ISO 105-X12	Grey scale 1/5	dry: 4 wet: 3/4
Dimensional change after washing UNI EN ISO 6330	Narrowing (weft): Shortening (warp):	
Dimensional change after dry cleaning UNI EN ISO 3175	Narrowing (weft): <= +-3% Shortening (warp): <= +-3%	
Resistance to Tearing UNI EN ISO 13937-3	> 150 N	
Resistance to yarn Slippage at stitched seams UNI EN ISO 13937-3 (din 14465)	weft mm < 6 warp mm < 6	



Nota: I rilievi effettuati in laboratorio s'intendono sempre indicativi.