## Date: December 02,2022 Page 1 of 4

Consignor	GUANGDONG ZHIDA TEXTILE DECORATION CO., LTD.
Consignor address	ZHIDA INDUSTRIAL PARK, NO. 1, RUIYUAN SOUTH ROAD, LONGFENG AVENUE, LONGJIANG TOWN, SHUNDE DISTRICT, FOSHAN CITY, GUANGDONG PROVINCE,China
THIS REPORT IS THE ENGL 2022-11-30	ISH VERSION OF THE TEST REPORT NO. SL92229330492101TX, DATE:
Sample Description by Client	SOFA FABRIC
Color	(A)NAIXE
Fiber Content/Material	(A)100%Polyester
The above sample(s)/ client inform	nation was/ were submitted and identified on behalf of the client as.
Sample status	Normal condition
Test Type/Sample Submitted by	Entrust Test (Sample Submitted by client)
Sample Receiving Date	Nov 23 2022
Testing Period	Nov 23 2022- Nov 30 2022
Document Accordance	Details please see test result page
Judgement Accordance	Client's Requirement
Test Conclusion	The report only give the test result and Individual Judgment, detail please see follow page, the results only apply to the sample(s) as received.

Test Items	А	Remark
Colour Fastness To Rubbing	PASS	
Abrasion Resistance	See Results	
Pilling Resistance	PASS	

Date: December 02,2022

Page 2 of 4

#### Test Results and Judgment

#### <u>Test items</u>

TestItem & Test method	Judgment	Sample	Unit	Requirement	Test F	Result
Colour Fastness To Rubbing	PASS	Α	Grade	≥4	Dry Staining	4-5
GB/T 3920-2008			Grade	≥4	Wet Staining	4-5

#### Abrasion Resistance

(ISO 12947-2: 2016; Martindale Abra	asion & Pilling	Tester, Pressure: 12kF	Pa)
-	Unit	(A)	Requirement
The quoted result	Rubs	Exceeds 100000	-

#### Pilling Resistance

(ISO 12945-2:2020;Martindale Abrasion & Pilling Tester, Total load applied 415g)

#### As Received

AILER SOU REVOLUTIONS			
-	Unit	Α	Requirement
Pilling Rating	-	5	≥4
Fuzzing Rating	-	5	≥4
Matting Rating	-	5	≥4
After 1000 Revolutions			
-	Unit	Α	Requirement
Pilling Rating	-	5	≥4
Fuzzing Rating	-	5	≥4
Matting Rating	-	5	≥4
After 2000 Develutions			
After 2000 Revolutions			
Alter 2000 Revolutions	Unit	Α	Requirement
Pilling Rating	Unit -	<b>A</b> 4-5	Requirement ≥4
-	Unit - -		
- Pilling Rating	Unit - - -	4-5	≥4
- Pilling Rating Fuzzing Rating	- - -	4-5 4-5	≥4 ≥4
- Pilling Rating Fuzzing Rating Matting Rating	Unit - - Unit	4-5 4-5	≥4 ≥4
- Pilling Rating Fuzzing Rating Matting Rating	- - -	4-5 4-5 4-5	≥4 ≥4 ≥4
- Pilling Rating Fuzzing Rating Matting Rating <u>After 5000 Revolutions</u> -	- - -	4-5 4-5 4-5	≥4 ≥4 ≥4 Requirement

Remarks:

Grade Pilling Description

- 5 No change
- 4 Partially formed pills
- 3 Moderate pilling pills of varying size and density partially covering the specimen surface
- 2 Distinct pilling pills of varying size and density covering a large proportion of the specimen surface
- 1 Severe pilling pills of varying size and density covering the whole of the specimen surface

Grade Fuzzing Description

- 5 No change
- 4 Slight surface fuzzing
- 3 Moderate surface fuzzing
- 2 Distinct surface fuzzing
- 1 Dense surface fuzzing

Grade Matting Description

- 5 No change
- 4 Slight surface matting
- 3 Moderate surface matting
- 2 Distinct surface matting
- 1 Dense surface matting



The test report shall only be used for client scientific research, teaching, internal quality control, product research and development, ect... and just for client internal reference.



# NAIXE Categoria MICRO

è una pelliccetta di poliestere, con un pelo corto e riccio, un prodotto estremamente versatile. E' elastico. Facile per la pulizia e la smacchiatura, morbida al tatto.

NAIXE is a polyester fur, with a short, curly pile, an extremely versatile product, it is not stretchy. Easy to clean and stain, soft to the touch.