

SOFT NATURAL

ARTICLE - ARTICOLO:

SOFT NATURAL 2.0

cod. V035

DESCRIPTION - DESCRIZIONE:

RAW MATERIAL - MATERIA PRIMA

BOVINE LEATHER - PELLE BOVINA

ORIGIN - ORIGINE

BOVINI USA

THICKNESS - SPESSORE

mm. 1,9/2,1

TANNING PROCESS - CONCIA

WET BLUE

AVERAGE SIZE - TAGLIA MEDIA

M²: 5.4

GRAIN - GRANA

CORRECTED GRAIN - FIORE CORRETTO

EMBOSSING - STAMPA

DOLLARO AMERICANO

FINISHING - FINITURA

ILG SPA - TIPO SEMI ANILINA

PHYSICAL MECHANICAL CHARACTERISTICS	STANDARD REFERENCE	UNIT	MINIMUM REQUIRED
Tear strenght Resistenza strappo	ISO 3377-1:2012	N	20 N
Flexing endurance Resistenza flessione	ISO 5402-1:2012	mm	No finish crack after 50000 cycles*
Cold Crack resistance of finish	ISO 17233:2005	°C	No finish crack at -10°C
Finish adhesion wet and dry Adesione rifinitura a umido e secco	ISO 11644:2009	N/cm	2 N/cm

* NOT APPLICABLE TO ANILINE LEATHER - NON APPLICABILE A PELLE ANILINA

COLOR FASTNESS TO LIGHT	STANDARD REFERENCE	MEASUREMENT'S UNIT	MINIMUM REQUIRED
Aniline, sued, nabuck	ISO 105-B02:2014	Blue scale	3
Semi aniline	ISO 105-B02:2014	Blue scale	4
Pigmented	ISO 105-B02:2014	Blue scale	5

To maintain the quality of the leather, please note the following tips

Consigli per mantenere inalterata la qualità della pelle.

Avoid placing leather under direct sun

Evitare la luce diretta del sole

Keep the leather away from heat sources

Evitare l'esposizione a fonti di calore

Remove the dust regularly with a soft and dry cloth

Spolverare regolarmente la pelle con un panno morbido ed asciutto

Recommended cleaning instructions

Istruzioni per pulire la pelle

Spots can be washed off using a lightly damp cloth with mild soap

Eventuali macchie si possono eliminare usando un panno inumidito con acqua e sapone neutro

Dry immediately after the treatment

Asciugare immediatamente dopo il trattamento

Do not rub. Use a circular motion working toward the centre of the stain

Non strofinare, ma tamponare delicatamente dai bordi al centro della macchia

RUBBING	STANDARD REFERENCE	MEASUREMENT'S UNIT	PIGMENTED		SEMIANILINE		ANILINE, NABUCK	
			CYCLES	VALUE	CYCLES	VALUE	CYCLES	VALUE
Dry	ISO 11640:2013	Grayscale	500	4	500	4	50	3
Wet	ISO 11640:2013	Grayscale	250	3/4	80	3	20	3
Perspiration	ISO 11640:2013	Grayscale	80	3/4	50	3/4	20	3

